

PIERI[®] Decobio C-23

Vegetable based concrete release agent

Description

PIERI[®] Decobio C-23 is dilutable with water, the resultant emulsion giving positive, blemish free release for both site cast and precast concrete.

The product is not classified as hazardous according to CLP/GHS. It is biodegradable and environmentally friendly compared to many alternative products. The unique packaging and mixing process minimises wastage and the need for drum storage or return costs.

Preparation

The concentrate is packed in 1 litre plastic sachets, cutoff corner and pour into a 5 litre (or larger capacity) sprayer. Add 4 litres of clean water, shake to instantly produce 5 litres of emulsion, ready for immediate use.

Immediately after application PIERI[®] Decobio C-23 emulsion forms a continuous film of oil on metal, plastic or sealed timber moulds. The film is not sensitive to rainwater when dried and has very high anti-adhesive powers giving excellent release and minimising surface blemishes, especially blowholes and colour staining.

Applications

Construction Sites:

Specially recommended for site use on most types of form work. The product hazards are reduced compared to many alternative products due to the absence of solvents and mineral oils.

Precast factories:

Recommended for its safety and ease of spray application especially in spaces where flammable products are restricted.

Particularly useful on concretes which subsequently are to be acid etched or sandblasted, as even if «overapplied» the resultant concrete surface finish is sound i.e. without dusting or damage sometimes caused by the misuse of the release agent.

Directions for use

The emulsion is stable for 2 hours, so it is always best to shake the sprayer before each application to reform an instant emulsion. In very cold weather, when dilution with water is not possible, it is recommended to use PIERI[®] Decobio C-23 neat in a very thin film (approximately 30 m²/litre) directly on to the mould by sponge or cloth.

Always protect the diluted emulsion from frost. Stores prayer in warm area. NB: the concentrate does not freeze until -10°C.

Advantages

- Far less storage space needed
- Less wastage and easy to use
- No 'bottom of tank' losses
- Storage and return of empty drums eliminated

Precautions

Preliminary on-site tests should be carried out for difficult or special conditions of casting.

Technical specifications

- Liquid concentrate, colour: Limpid
- Density: 0.95 ± 0.03
- Viscosity: 60 – 90 centipoise (ISO 2431)
- Constituents: Entirely of natural products.
- Does not contain any petroleum derivatives, mineral oil, paraffin, wax or alcohols'
- Flash point: $>160^{\circ}\text{C}$
- Boiling point: $>250^{\circ}\text{C}$
- Freezing point: -10°C (not diluted)
- Vapour pressure: < 0.1 millibar
- Approximate consumption: $30 \text{ m}^2/\text{l}$ (emulsion) or $150 \text{ m}^2/\text{l}$ (concentrate)
- Biodegradability 98 % within 21 days (STURM Test in accordance with the instruction 92/69/CEE).
- Recommended PIERI[®] nozzles: X 10 or standard (fan nozzle)

Storage

2 years in original unopened packaging.

Packaging

1 litre in polyethylene sachets

20 x 1 litre in a carton

25 litres drum

Safety

Read and understand the product label and Safety Data Sheet (SDS) prior to working with the product and follow the precautionary statements.

SDSs can be obtained by contacting your local GCP representative or office.

Transport

Not regulated.

gcpat.com | For technical information: asia.enq@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

PIERI® is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA.
22Xuan Thoi Son Village, Hoc Mon District, Ho Chi Minh City.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Vietnam Company Ltd, Lot B14, Section B, Street No. 12, Xuan Thoi Son Small Scale Arts & Crafts Group, National Road 22Xuan Thoi Son Village, Hoc Mon District, Ho Chi Minh City

This document is only current as of the last updated date stated below and is valid only for use in Vietnam. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.vn. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-01-28

gcpat.vn/solutions/products/pieri-architectural-precast-portfolio/pieri-decobio-c-23