

WRDA[®] 96M

Water-reducing initial set retarder

Product Description

WRDA[®]96M is a high performance, ready-to-use liquid admixture, formulated from selected purity lignosulphonates and modified polymers. Ingredients are factory premixed in exact proportions to minimise handling, eliminate mistakes and guesswork. WRDA 96M is formulated to comply with the following chemical admixture specifications for concrete: ASTM C 494, Type B and D; BS 5075: Part 1; SS 320: 1987.

One litre of WRDA 96M weighs approximately 1.08kg ± 0.02kg.

Application

WRDA 96M retards the initial and final set of concrete. At the usual addition rate of 300mL / 100kg cementitious material it will extend the initial setting time of portland cement concrete by 2 to 3 hours at 21 °C. WRDA 96M is used wherever a delay in setting time is required to insure sufficient delivery, placement, vibration or compaction time, such as in:

- Hot Weather Concreting
- Transit Mix Concrete
- Prestressed Concrete

WRDA 96M is also used in special applications, as in bridge decks where it extends plastic characteristics of the concrete until progressive deflection resulting from increasing loads is completed.

Addition Rates

Addition rates for WRDA 96M will typically range from 200 to 600mL / 100kg of cementitious material. The amount to be used will depend upon the degree of retardation required under job conditions. Longer setting times or higher temperatures will require higher addition rates. Conversely, the addition rate will be lower for shorter extensions of time.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.

Packaging

WRDA 96M is available in bulk and 205L drums. It contains no flammable ingredients. WRDA 96M will freeze at about -2 °C, but will return to full strength after thawing and thorough agitation.



Water-reducing Properties

Along with set retardation, WRDA 96M provides water-reduction (typically 8 to 12%) in a concrete mix. This water-reducing action of WRDA 96M produces greater plasticity and workability in the fresh concrete and the strength and permeability of the hardened concrete are measurably improved. WRDA 96M is designed for use on jobs where high temperatures make extended setting times desirable. It is recommended only when the primary purpose is to delay and control the setting time of concrete. When time and temperature are not major considerations, water-reducing admixtures from GCP Applied Technologies should be used. Please consult our representative for the most appropriate admixture for your project application.

Compatibility with Other Admixtures

WRDA 96M is compatible in concrete with all commercial air-entraining admixtures, such as DARAVAIR® or DAREX® AEA®. Due to the slight air-entraining properties of WRDA 96M itself, the addition rate of Daravair may be reduced by about 25%. By combining the separate effects of air entrainment and dispersion, the water requirement of concrete may be

Health and Safety

See WRDA 96M Material Safety Data Sheet or consult GCP Applied Technologies.

gcpat.vn | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India: Chennai +91 44 6624 2308 Delhi +91 124 402 8923 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

WRDA, Daravair, Darex, HYCOL and AEA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

Printed in Singapore | 03/16 | 200-WRDA-276

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Vietnam Company Ltd, Lot B14, Section B, Street No. 12, Xuan Thoi Son Small Scale Arts & Crafts Group, National Road 22Xuan Thoi Son Village, Hoc Mon District, Ho Chi Minh City

This document is only current as of the last updated date stated below and is valid only for use in Vietnam. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.vn. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-10-13

gcpat.vn/solutions/products/wrda-96m